

ECOZEN® T95

Bio-based Copolyester

SK Chemicals

Message:

ECOZEN® T95 is a Bio-based Copolyester material. It is available in Asia Pacific, Europe, or North America.

Important attributes of ECOZEN® T95 are:

Flame Rated

Eco-Friendly/Green

General Information			
UL YellowCard	E215991-100521458		
Features	Renewable Resource Content		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.30	%	ASTM D955
Water Absorption (Equilibrium)	0.20 to 0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	51.0	MPa	
Break	42.0	MPa	
Tensile Elongation ²			ASTM D638
Yield	5.7	%	
Break	150	%	
Flexural Modulus ³	2130	MPa	ASTM D790
Flexural Strength ⁴	86.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	85.0	°C	ASTM D648
Glass Transition Temperature	95.0	°C	ASTM E1356
Flammability	Nominal Value		Test Method
Flame Rating (3.20 mm)	V-2		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.560		ASTM D542
Transmittance	90.0	%	ASTM D1003
Haze	< 1.0	%	ASTM D1003
NOTE			
1.	50 mm/min		

2.	50 mm/min
3.	1.3 mm/min
4.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

