

Petrothene® M2520FNx02

Low Density Polyethylene

LyondellBasell Industries

Message:

PETROTHENE M2520 is a film grade resin that exhibits excellent optics, good gloss, good bubble stability and outstanding processability. A typical application for this resin is high clarity packaging that requires higher modulus.

General Information			
Additive	Antiblock (1000 ppm)		
	Slip (800 ppm)		
Features	Antiblocking		
	Food Contact Acceptable		
	Good Processability		
	High Clarity		
	High Gloss		
	Opticals		
	Slip		
Uses	Film		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.925	g/cm ³	ASTM D1558
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	ASTM D882
Secant Modulus			
1% Secant, MD : 25 µm, Blown Film	269	MPa	
1% Secant, TD : 25 µm, Blown Film	338	MPa	ASTM D882
Tensile Strength			
MD : Yield, 25 µm, Blown Film	11.7	MPa	
TD : Yield, 25 µm, Blown Film	13.1	MPa	ASTM D882
MD : Break, 25 µm, Blown Film	29.6	MPa	
TD : Break, 25 µm, Blown Film	22.8	MPa	
Tensile Elongation			ASTM D882
MD : Break, 25 µm, Blown Film	130	%	

TD : Break, 25 µm,Blown Film	470	%	
Dart Drop Impact (25 µm, Blown Film)	75	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm, Blown Film	270	g	
TD : 25 µm, Blown Film	80	g	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.4 µm, Blown Film)	70		ASTM D2457
Haze (25.4 µm, Blown Film)	5.5	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

