

# UBE Nylon 1022 C2

Polyamide 6

UBE Engineering Plastics, S.A.

## Message:

UBE NYLON 1022 C2 is a high viscosity, nanocomposite-modified Polyamide 6, offering excellent barrier properties. The material is suitable for cast and air-cooled blown film production.

General Information			
Filler / Reinforcement	Nanofiller		
Features	Workability, good		
	Definition, high		
	Compliance of Food Exposure		
	Viscosity, High		
	Barrier resin		
Uses	Films		
Agency Ratings	FDA Food Exposure, Not Rated		
	European food contact, not rated		
Forms	Particle		
Processing Method	Blow film		
	cast film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ASTM D1894
With self-dynamics	0.30		ASTM D1894
With Self-Static	0.30		ASTM D1894
Films	Nominal Value	Unit	Test Method
Secant Modulus - MD (Cast Film)	1050	MPa	ASTM D882
Tensile Strength - MD			ASTM D882
Yield, extruded film	38.0	MPa	ASTM D882
Fracture, extruded film	100	MPa	ASTM D882
Tensile Elongation - MD (Fracture, Extruded Film)	450	%	ASTM D882
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	215	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Optical	Nominal Value	Unit	Test Method

Gardner Gloss	140		ASTM D523
Haze	1.5	%	ASTM D1003

#### Additional Information

The value listed as Surface Resistivity, ASTM D257, was tested in accordance with UBE test methods. Oxygen Permeability, ASTM D3985: 24 ml/m<sup>2</sup>/day Relative Viscosity, JIS K6810, 96% H<sub>2</sub>SO<sub>4</sub>, conc. 1.0 g/100 ml: 3.54 Extractable Content, JIS K6810: <1.00 wt% Water Vapor Permeability, JIS Z0208: 60 g/m<sup>2</sup>/day Piercing Strength, JAS P1019, Cast Film: 10.5 N Piercing Elongation, JAS P1019, Cast Film: 12 mm Flex Crack Resistance, MIL B131B, 23°C, 1000 cycle, Cast Film: <30 hole/0.04 m<sup>2</sup> Gelbo Test, MIL B131B, 5°C, 100 cycle, Cast Film: <15 hole/0.04 m<sup>2</sup>

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

