

RTP 2500 A HB

Polycarbonate + ABS

RTP Company

Message:

Unfilled - UL94 HB

General Information			
UL YellowCard	E84658-251333		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.80	%	ASTM D955
Moisture Content	0.020	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2760	MPa	ASTM D638
Tensile Strength	58.6	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	2760	MPa	ASTM D790
Flexural Strength	96.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	640	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	No Break		ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	110	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	93.3	°C	
Drying Time	4.0	hr	
Dew Point	-28.9	°C	
Processing (Melt) Temp	243 - 274	°C	
Mold Temperature	51.7 - 93.3	°C	
Injection Pressure	68.9 - 103	MPa	
Injection instructions			

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT