

CYCOLOY™ CM6210 resin

Polycarbonate + ABS

SABIC Innovative Plastics

Message:

CYCOLOY resin CM6210 is a high-modulus flame retardant PC/ABS with non-brominated and non-chlorinated FR system. It can be used for extrusion & thermoforming applications and also for injection molding applications where higher stiffness is needed.

General Information			
UL YellowCard	E207780-462513		
Additive	Flame retardancy		
Features	Chlorine Free		
	Rigidity, high		
	Bromine-free		
	Flame retardancy		
Processing Method	Sheet extrusion molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.28	g/cm ³	ASTM D792
--	1.27	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	12	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	9.00	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.60	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.30	%	ISO 62
Equilibrium, 23°C, 50% RH	0.10	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	98		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	3570	MPa	ASTM D638
--	3660	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	64.0	MPa	ASTM D638
Yield	59.7	MPa	ISO 527-2/5
Yield	63.0	MPa	ISO 527-2/50
Fracture ³	50.0	MPa	ASTM D638
Fracture	65.0	MPa	ISO 527-2/5
Fracture	50.0	MPa	ISO 527-2/50
Tensile Elongation			

Yield ⁴	4.9	%	ASTM D638
Yield	3.6	%	ISO 527-2/5
Yield	3.5	%	ISO 527-2/50
Fracture ⁵	80	%	ASTM D638
Fracture	100	%	ISO 527-2/5
Fracture	97	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	3500	MPa	ASTM D790
-- ⁷	3560	MPa	ISO 178
Flexural Stress			
--	106	MPa	ISO 178
Yield, 50.0mm span ⁸	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	10	kJ/m ²	ISO 179/1eA
23°C	45	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	90	J/m	ASTM D256
23°C	500	J/m	ASTM D256
-30°C ¹⁰	10	kJ/m ²	ISO 180/1A
23°C ¹¹	45	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	45.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, unannealed, 100 mm span ¹²	99.0	°C	ISO 75-2/Be
1.8 MPa, unannealed, 3.20mm	90.0	°C	ASTM D648
1.8 MPa, unannealed, 100 mm span ¹³	89.0	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	106	°C	ASTM D1525 ¹⁴
--	112	°C	ISO 306/B50
--	114	°C	ISO 306/B120
Ball Pressure Test			IEC 60695-10-2
75°C	Pass		IEC 60695-10-2
95°C ¹⁵	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			
Flow: -40 to 40°C	5.7E-5	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	5.2E-5	cm/cm/°C	ISO 11359-2
Flow: 23 to 60°C	5.2E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	7.0E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	6.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 60°C	6.0E-5	cm/cm/°C	ISO 11359-2

Thermal Conductivity	0.30	W/m/K	ISO 8302
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI	60.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength			IEC 60243-1
0.800mm, in oil	38	kV/mm	IEC 60243-1
1.60mm, in oil	26	kV/mm	IEC 60243-1
3.20mm, in oil	17	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
50 Hz	2.90		IEC 60250
60 Hz	2.90		IEC 60250
1 MHz	2.80		IEC 60250
Dissipation Factor			IEC 60250
50 Hz	3.0E-3		IEC 60250
60 Hz	3.0E-3		IEC 60250
1 MHz	4.0E-3		IEC 60250
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Extrusion	Nominal Value	Unit	
Drying Temperature	82.2 - 87.8	°C	
Drying Time	3.0 - 4.0	hr	
Cylinder Zone 1 Temp.	182 - 227	°C	
Cylinder Zone 2 Temp.	188 - 232	°C	
Cylinder Zone 3 Temp.	204 - 241	°C	
Cylinder Zone 4 Temp.	210 - 243	°C	
Adapter Temperature	210 - 243	°C	
Melt Temperature	221 - 243	°C	
Die Temperature	210 - 243	°C	
Extrusion instructions			
Drying Time (Cumulative): 12 hrsMinimum Moisture Content: 0.04 %Roll Stack Temp - Bottom: 66 - 88 °CRoll Stack Temp - Middle: 71 - 93 °CRoll Stack Temp - Top: 71 - 99 °C			
NOTE			
1.	5.0 mm/min		
2.	Type 1, 5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	Type 1, 5.0 mm/min		
5.	Type 1, 5.0 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		

9.	80*10*3 sp=62mm
10.	80*10*3
11.	80*10*3
12.	120*10*4 mm
13.	120*10*4 mm
14.	标准 B (120°C/h), 载荷2 (50N)
15.	Approximate maximum

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

