# Vipel® F701-RRR-00

### Polyester Alloy

AOC, L.L.C.

#### Message:

AOC's Vipel F701 Series resins are high molecular weight, two-stage isophthalic, unsaturated polyester resin with the wet out, cure and handling characteristics of general purpose resins.

They have an excellent shelf life and are ideal for filament winding and spray-up. A few selected resins are listed below including the high viscosity base resin, Vipel F701-FHG-00.

**BENEFITS** 

Corrosion resistance

General Information

AOC's Vipel F701 series resins provide excellent corrosion resistance when used in contact with inorganic and organic acids. Solvent resistance is field-proven for many petroleum products such as kerosene, heating oil and crude oils.

Refer to AOC's "Corrosion Resistant Resin Guide" for corrosion resistance information or for questions regarding suitability of a resin to any particular chemical environment contact AOC.

Versatile

Suitable for various fabricating methods such as hand lay-up, spray-up and filament winding.

Features	High molecular weight									
	m-benzene dimethyl  Solvent resistance  Good corrosion resistance  acid resistance  Oil resistance									
						Agency Ratings	FDA 21 CFR 177.2420			
						Forms	Liquid			
						Processing Method	Filament power winding			
Sprayable										
Hand coating										
Physical	Nominal Value	Unit	Test Method							
Styrene Content	38	%								
Gel to Peak	2.0	min								
Peak Exotherm	210	°C								
Hardness	Nominal Value	Unit	Test Method							
Barcol Hardness	43		ASTM D2583							
Mechanical	Nominal Value	Unit	Test Method							
Tensile Modulus	3790	МРа	ASTM D638							
Tensile Strength	83.4	МРа	ASTM D638							
Tensile Elongation (Break)	2.8	%	ASTM D638							
Flexural Modulus	4210	МРа	ASTM D790							
Flexural Strength	127	МРа	ASTM D790							
Thermal	Nominal Value	Unit	Test Method							

Deflection Temperature Under Load (1. MPa, Unannealed)	8 107	°C	ASTM D648
Uncured Properties	Nominal Value	Unit	
Density	1.10	g/cm³	
Viscosity (Brookfield RVT)	1.2	Pa·s	
Gel Time (82°C)	6.7	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

