Geon™ Vinyl Rigid Extrusion L7416

Rigid Polyvinyl Chloride

PolyOne Corporation

Message:

Geon[™]Vinyl Rigid Extrusion L7416 is a rigid PVC product. It can be processed by extrusion and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Geon[™]The application areas of Vinyl Rigid Extrusion L7416 include outdoor applications and architectural applications.

Features include: Impact resistance

good weather resistance

General Information					
Features	Impact resistance, high				
	Good weather resistance				
Uses	Doors and Windows				
	Outdoor application				
	Profile				
Forms	Particle				
Processing Method	Extrusion				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.45	g/cm³	ASTM D792		
PVC Cell Classification	1-31432-33		ASTM D4216		
PVC Cell Classification	13344		ASTM D1784		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D, 15 sec)	82		ASTM D2240		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Modulus ¹	2480	MPa	ASTM D638		
Tensile Strength ² (Yield)	44.1	MPa	ASTM D638		
Flexural Modulus	2960	MPa	ASTM D790		
Flexural Strength	84.8	МРа	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact			ASTM D256A		
23°C, 3.18mm, injection molding	160	J/m	ASTM D256A		
Transverse flow: 23°C, 3.18mm, molded	160	J/m	ASTM D256A		
Flow: 23°C, 3.18mm, molded	150	J/m	ASTM D256A		
Drop Impact Resistance			ASTM D4226		
23°C ³	53.4	J/cm	ASTM D4226		
23°C ⁴	178	J/cm	ASTM D4226		
Thermal	Nominal Value	Unit	Test Method		

Deflection Temperature Under Load (1.8				
MPa, Unannealed, 3.18 mm)	72.8	°C	ASTM D648	
CLTE - Flow	6.1E-5	cm/cm/°C	ASTM D696	
Additional Information	Nominal Value			
Ease of Sizing	Acceptable			
注释:分档是采用注塑模制样品进行缺口摆锤冲击试验确定的.				
Extrusion	Nominal Value	Unit		
Melt Temperature	182 - 193	°C		
NOTE				
1.	Type 1, 5.1 mm/min			
2.	Type 1, 5.1 mm/min			
3.	Procedure A, C.125 Throwing			
4.	Procedure B, C.125 Throwing			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

