

# Luran® SAN C

Styrene Acrylonitrile

Styrolution

## Message:

Luran SAN C is an injection molding grade of SAN with medium impact strength and high flow.

General Information			
UL YellowCard	E256400-520833		
Features	High Flow		
	Medium Impact Resistance		
Uses	Appliances		
	Electrical/Electronic Applications		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	23.0	cm <sup>3</sup> /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	68.0	MPa	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	104	°C	ASTM D1525 <sup>1</sup>
NOTE			
1.	Rate B (120°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT