

LUMISIL® 868

Silicone
Wacker Chemie AG

Message:
Silicone Rubber, RTV-2
Optoelectronics, Lighting
Optoelectronics, Electronics
Potting Compound, Electronics
LED, Lighting

General Information			
Uses		LEDs Lighting Applications	
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.05	g/cm ³	ISO 2781
Pot Life	> 960	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	77		ISO 868
Tensile Strength	8.00	MPa	ISO 37
Tensile Elongation at Break	70	%	ISO 37

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT