

NYCOA Polyamide 2062

Polyamide 66/6 Copolymer

Nycoa (Nylon Corporation of America)

Message:

NYCOA 2062 is a Nylon copolymer suitable for injection molding and extrusion. This copolymer offers an excellent balance of mechanical properties and outstanding processability. Its lower melting point, greater flexibility, and lower crystallinity than standard nylon resins, makes it ideal for a variety of extrusion applications. In addition, the high relative viscosity provides excellent melt strength and toughness after process NYCOA 2062 complies with all the requirements of the FDA regulations 21 CFR 177.1500. NYCOA 2062 typical applications include barrier films and tubing.

General Information			
Features	Copolymer		
	Workability, good		
	Good melt strength		
	Good flexibility		
	Good toughness		
	Medium and high viscosity		
Uses	Films		
	Pipe fittings		
Agency Ratings	FDA 21 CFR 177.1500		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Water Absorption (24 hr)	1.7	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	72.4	MPa	ASTM D638
Tensile Elongation ² (Break)	200	%	ASTM D638
Flexural Modulus ³	2370	MPa	ASTM D790
Flexural Strength ⁴	89.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (6.35 mm)	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	199	°C	DSC
Additional Information			
Relative Viscosity, NYCOA Method: 4 SAVWater Extractable, NYCOA Method: 0.8 %Tensile Elongation at Break, ASTM D638, 2 in/min: 200+%The value listed as Melting Point DSC, was tested in accordance with ASTM D789.			

NOTE	
1.	51 mm/min
2.	51 mm/min
3.	51 mm/min
4.	51 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT