

# Mafill® CR CC 9349

Polypropylene Copolymer

Ravago Group

Message:

PPC Grey CF 20

General Information			
Filler / Reinforcement	Calcium Carbonate,20% Filler by Weight		
Recycled Content	Yes		
Features	Copolymer		
Appearance	Grey		
Physical	Nominal Value	Unit	Test Method
Density	1.03	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ISO 1133
Ash Content	20	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	22.0	MPa	ISO 527-2
Flexural Modulus	1600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	4.0	kJ/m <sup>2</sup>	ISO 180/1A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

