

Mirathane™ E195

Thermoplastic Polyurethane Elastomer (Polyester)

Miracll Chemicals Co., Ltd.

Message:

Mirathane™ E195 is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) product. It is available in Asia Pacific. Applications of Mirathane™ E195 include coating applications, engineering/industrial parts, hose/tubing, additive/masterbatch and automotive.

Characteristics include:

- Chemical Resistant
- Good Flexibility
- Puncture Resistant
- Wear Resistant

General Information			
Features	Good Abrasion Resistance		
	Kink Resistant		
	Low Compression Set		
	Low Temperature Flexibility		
	Oil Resistant		
	Puncture Resistant		
	Solvent Resistant		
Uses	Automotive Applications		
	Belts/Belt Repair		
	Coating Applications		
	Compounding		
	Fabric Coatings		
	Film		
	Footwear		
	Hose		
	Overmolding		
	Seals		
	Sheet		
	Tubing		
	Wheels		
	Wire & Cable Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	95		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	35.0	mm ³	DIN 53516

Service Temperature	-20 to 90	°C	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	13.0 to 15.0	MPa	
300% Strain	25.0 to 35.0	MPa	
Tensile Strength (Yield)	38.0 to 42.0	MPa	ASTM D412
Tensile Elongation (Break)	350 to 400	%	ASTM D412
Tear Strength	120 to 150	kN/m	ASTM D624
Compression Set			ASTM D395
23°C, 72 hr	30	%	
70°C, 22 hr	35 to 50	%	
100°C, 24 hr	45	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ¹	-30.0	°C	ASTM D3417, DSC
Extrusion	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0 to 4.0	hr	
Cylinder Zone 1 Temp.	210	°C	
Cylinder Zone 2 Temp.	205	°C	
Cylinder Zone 3 Temp.	200	°C	
Die Temperature	215	°C	
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT