

Gallonprene® GP520-8501

Thermoplastic Elastomer

Shenzhen Sungallon Rubber & Plastic Corporation Limited

Message:

Gallonprene® GP520-8501 is a thermoplastic elastomer (TPE) product. It can be processed by injection molding and is available in Africa and the Middle East, Latin America or Asia Pacific. Gallonprene® GP520-8501 application areas include engineering/industrial accessories, home applications and handles.

Features include:

Comply with REACH standard

ROHS certification

Halogen-free

| General Information | | | |
|---|-------------------------|-------------------|-------------|
| Features | High elasticity | | |
| | Halogen-free | | |
| Uses | O-rings | | |
| | overmolding | | |
| | Household goods | | |
| | Soft handle | | |
| Agency Ratings | EC 1907/2006 (REACH) | | |
| RoHS Compliance | RoHS compliance | | |
| Appearance | White | | |
| | Rough surface polishing | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.978 | g/cm ³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (200°C/2.16 kg) | 16 | g/10 min | ASTM D1238 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 23°C) | 85 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ (Break) | 7.50 | MPa | ASTM D412 |
| Tensile Elongation ² (Break) | 700 | % | ASTM D412 |
| Injection | Nominal Value | Unit | |
| Rear Temperature | 140 - 160 | °C | |
| Middle Temperature | 150 - 170 | °C | |
| Front Temperature | 160 - 180 | °C | |
| Processing (Melt) Temp | 110 - 130 | °C | |
| Mold Temperature | 30.0 - 60.0 | °C | |
| Injection Rate | Moderate | | |

Injection instructions

Processing Temperature Limit: 260°C Injection Pressure: Moderate Back Pressure: 20 to 50% Overmolding Parameters: Rear Temperature: 160 to 180°C Center Temperature: 170 to 190°C Front Temperature: 180 to 200°C Melt Temperature: 110 to 130°C Mold Temperature: 30 to 60°C Processing Temperature Limit: 220°C Injection Pressure: Moderate Injection Speed: Moderate Back Pressure: 20 to 50%

NOTE

- | | |
|----|------------|
| 1. | 500 mm/min |
| 2. | 500 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT