

# Eltex® P KS359

Polypropylene Random Copolymer

INEOS Olefins & Polymers Europe

## Message:

### Benefits & Features

ELTEX® P KS359 offers a very low heat seal temperature (10°C below that of ELTEX® P KS400 type random copolymers) and contains no technical additives. It is thus particularly appreciated by users wishing to use their own "formulas".

It is developed primarily for the sealing layer in "coextruded bioriented film" for food and technical packaging.

### Applications

2nd generation terpolymer specially developed for the sealing layers of "coextruded bioriented film", suitable also for coextruded cast film

General Information			
Features	Food Contact Acceptable		
	Low Temperature Heat Sealability		
	Terpolymer		
Uses	Bi-axially Oriented Film		
	Cast Film		
	Film		
	Food Packaging		
	Packaging		
RoHS Compliance	Contact Manufacturer		
Forms	Pellets		
Processing Method	Cast Film		
	Coextrusion		
	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.895	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 23°C)	58		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	20.0	MPa	ISO 527-2
Flexural Modulus (23°C)	620	MPa	ISO 178
Films	Nominal Value	Unit	Test Method
Heat Seal Threshold <sup>1</sup>	105	°C	Internal Method
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	55.0	°C	ISO 75-2/B

Vicat Softening Temperature	105	°C	ISO 306/A50
Peak Melting Temperature	131	°C	ASTM D3417

NOTE

1. 1s, 3 bars, 100 mm/min, 100 g/cm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

