## Daelim Po1y® VL0003 Shoe Sole

## Ethylene-based Plastomer

DAELIM INDUSTRIAL CO., LTD.

## Message:

Daelim Po1y®VL0003 Shoe Sole is a vinyl plastic product. It is available in Europe or Asia Pacific. Daelim Po1y®VL0003 Shoe Sole's application areas include consumer goods and food contact applications. Features include: Good processability Antioxidants Good tear strength Wear-resistant Heat resistance

General Information				
Additive	Antioxidation			
Features	Low density			
	Antioxidation			
	Workability, good			
	Good heat aging resistance			
	Good tear strength			
	Good wear resistance			
	The smell is low to none			
Uses	Footwear			
Agency Ratings	FDA 21 CFR 177.1520			
Physical	Nominal Value	Unit	Test Method	
Density	0.900	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (190°C/2.16				
kg)	3.0	g/10 min	ASTM D1238	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness			ASTM D2240	
Shore A, Molded	86		ASTM D2240	
Shore D, Molded	40		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break, Compression Molded)	30.4	MPa	ASTM D638	
Tensile Elongation (Break, Compression Molded)	800	%	ASTM D638	
Flexural Modulus (Compression Molded)	68.6	MPa	ASTM D790	
Elastomers	Nominal Value	Unit	Test Method	
Tear Strength	73.5	kN/m	ASTM D624	
Thermal	Nominal Value	Unit	Test Method	
Vicat Softening Temperature	82.0	°C	ASTM D1525	

Peak Melting Temperature	86.0 - 97.0	°C	ASTM D3418
Injection	Nominal Value	Unit	
Processing (Melt) Temp	90 - 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

