

SPESIN® KP212G15V0W3

Polybutylene Terephthalate

Kolon Plastics, Inc.

Message:

SPESIN® KP212G15V0W3 is a Polybutylene Terephthalate (PBT) product filled with 15% glass fiber. It is available in North America.

Characteristics include:

Flame Rated

Flame Retardant

Good UV Resistance

Good Weather Resistance

General Information			
UL YellowCard	E190675-100647279		
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good UV Resistance		
	Good Weather Resistance		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60 to 1.4	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.060	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	93.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	7.0	%	ASTM D638
Flexural Modulus (23°C)	5490	MPa	ASTM D790
Flexural Strength (23°C)	167	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	215	°C	
1.8 MPa, Unannealed	178	°C	
Melting Temperature	224	°C	ASTM D1525
CLTE - Flow	4.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	26	kV/mm	ASTM D149

Dielectric Constant (1 MHz)	3.50		ASTM D150
Arc Resistance	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

