

Kuraray K-Polymer KL-318

Polyvinyl Alcohol
Kuraray Co., Ltd.

Message:
Modified

General Information			
Features	Biodegradable		
	Water Soluble		
Uses	Adhesives		
	Paper Coatings		
Forms	Granules		
Physical	Nominal Value	Unit	Test Method
Solution Viscosity ¹	20 to 30	mPa · s	DIN 53015
Volatile Matter	5.0	%	
Degree of Hydrolysis	85 to 90	%	
NOTE			

1. 4 % aqueous solution at 20 °C
determined by Brookfield
synchronized-motor rotary-type
visometer

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

