

XYFLUOR® 860

Fluoroelastomer
Greene, Tweed & Co.

Message:

Xyfluor® 860, a highly fluorinated elastomer compound, offers excellent chemical compatibility over a wide range of temperatures from -76°F to 450°F (-60°C to 232°C). Recommended for applications requiring a combination of low temperature properties and chemical resistance, Xyfluor's capabilities surpass those of standard fluoroelastomers, PTFE and graphite. Additionally, Xyfluor reduces overall cost by extending equipment service life.

General Information			
Features	Good Chemical Resistance		
	Hydrocarbon Resistant		
	Low Temperature Resistant		
	Steam Resistant		
Uses	Gaskets		
	Pump Parts		
	Seals		
	Valves/Valve Parts		
Appearance	Black		
Forms	Pellets		
Processing Method	Compression Molding		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore A)	70		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	2.41	MPa	ASTM D1414
Tensile Strength (Break)	6.89	MPa	ASTM D1414
Tensile Elongation (Break)	250	%	ASTM D1414
Compression Set ¹ (200°C, 70 hr)	30	%	ASTM D395
Thermal	Nominal Value	Unit	
Service Temperature	-60 to 232	°C	
NOTE			
1.	25% Deflection		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

