

Dynaprene® SE0035A

Thermoplastic Elastomer

Nantex Industry Co., Ltd.

Message:

Dynaprene® SE0035A is a Thermoplastic Elastomer (TPE) material. It is available in Asia Pacific for injection molding.

General Information			
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.888	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	35		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress - Across Flow (300% Strain)	1.79	MPa	ASTM D412
Tensile Strength - Across Flow (Yield)	2.96	MPa	ASTM D412
Tensile Elongation - Across Flow (Break)	490	%	ASTM D412
Tear Strength ¹ (23°C)	13.1	kN/m	ASTM D624
Compression Set			ASTM D395B
23°C, 22 hr	9.0	%	
70°C, 22 hr	31	%	
NOTE			

1. Die C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT