

Celanex® 5206HG

Polyethylene Terephthalate

Celanese Corporation

Message:

Celanex 5206HG is a 15% glass-filled polyester featuring super high surface gloss and high flow for long flow channels. A typical application is oven handles.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Features	Highlight		
	High liquidity		
Uses	Handle		
Physical	Nominal Value	Unit	Test Method
Density	1.45	g/cm ³	ISO 1183
shrinkage-Flow	0.40 - 0.60	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6400	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	95.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	1.8	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	6300	MPa	ISO 178
Flexural Stress (23°C)	135	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.7	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	4.5	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	180	°C	ISO 75-2/A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

