

Trademark PP PPR3500MA

Polypropylene Random Copolymer

Trademark Plastics Corporation

Message:

Trademark PP PPR3500MA is a Polypropylene Random Copolymer (PP Random Copolymer) product. It can be processed by injection molding and is available in North America. Applications of Trademark PP PPR3500MA include containers, food contact applications, household applications and packaging.

Characteristics include:

- Antistatic
- Clarified
- Copolymer
- Food Contact Acceptable
- Good Aesthetics

General Information			
Additive	Antistatic		
	Clarifier		
Features	Antistatic		
	Food Contact Acceptable		
	Good Flow		
	Good Processability		
	Low to No Odor		
	Opticals		
	Random Copolymer		
Uses	Food Containers		
	Household Goods		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	25.2	MPa	ASTM D638
Tensile Elongation ² (Yield)	11	%	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	48	J/m	ASTM D256
Optical	Nominal Value	Unit	Test Method

Haze (1270 μm)	11	%	ASTM D1003
NOTE			
1.	51 mm/min		
2.	51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

