Spartech Polycom SCR1-5009

Acrylonitrile Butadiene Styrene

Spartech Polycom

Message:

Spartech SCR1-5009 is a low viscosity, ABS resin for injection molding. It is heat stabilized and lubricated for good processing characteristics, and it exhibits good impact and chemical resistance.

With the benefit of low moisture absorption, ABS can be used in a variety of environments. Being a very versatile product, SCR1-5009 can be used for industrial, transportation, sporting goods and electrical/electronic applications.

General Information					
Additive	heat stabilizer				
	Lubricant				
Features	Low hygroscopicity				
	Low viscosity				
	Impact resistance, good				
	Workability, good				
	Good chemical resistance				
	Thermal Stability				
	Thermal stability, good				
	Lubrication				
Uses	Electrical/Electronic Applications				
	Industrial application				
	Application in Automobile Field				
	Sporting goods				
Appearance	Available colors				
	Natural color				
Forms	Particle				
Processing Method	Injection molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.05	g/cm³	ASTM D792		
Melt Mass-Flow Rate (MFR)	14	g/10 min	ASTM D1238		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield, 23°C)	41.4	MPa	ASTM D638		
Flexural Modulus (23°C)	2210	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (23°C)	240	J/m	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		

Deflection Temperature Under Load (0.45 MPa, Unannealed)	5 92.5	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	87.8	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	210 - 240	°C	
Middle Temperature	215 - 245	°C	
Front Temperature	220 - 250	°C	
Nozzle Temperature	218 - 260	°C	
Processing (Melt) Temp	218 - 260	°C	
Mold Temperature	43.3 - 65.6	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

