

# NEOFLON™ M-300P

Polychlorotrifluoroethylene

DAIKIN AMERICA, INC.

## Message:

Pellets for extrusion and injection molding of rods and small parts.

General Information			
Uses	Rods		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.10 to 2.17	g/cm <sup>3</sup>	ASTM D1430
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	32.0 to 37.0	MPa	ASTM D1430
Tensile Elongation (Break)	50 to 200	%	ASTM D1430
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	210 to 212	°C	ASTM D1430
Additional Information	Nominal Value	Unit	Test Method
Zero Strength Time	3.3 to 5.0	min	ASTM D1430

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT