

LUVOCOM® 94-8485

Low Density Polyethylene

LEHVOSS Group

Message:

LUVOCOM® 94-8485 is a low density polyethylene material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

Typical application areas include:

engineering/industrial accessories

Tools

container

textile/fiber

Automotive Industry

General Information			
Uses	Thin wall parts		
	Textile applications		
	Engineering accessories		
	Machine/mechanical parts		
	Mould		
	Application in Automobile Field		
	Container		
	Business equipment		
	Food container		
	Mold/Mold/Tool		
Appearance	Natural color		
Physical	Nominal Value	Unit	Test Method
Density	1.57	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	> 50	g/10 min	ISO 1133
Molding Shrinkage	1.5 - 3.0	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	300	MPa	ISO 527-2
Tensile Stress (Break)	9.00	MPa	ISO 527-2
Tensile Strain (Yield)	20	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength			ISO 179/1fU
-30°C	No Break		ISO 179/1fU
23°C	No Break		ISO 179/1fU
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	70.0	°C	UL 746B

Maximum operating temperature-Short Term	100	°C	
Insulation Resistance	> 1.0E+9	ohms	IEC 60167
Vicat Softening Temperature	80.0	°C	ISO 306/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+9	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	85	°C	
Drying Time - Desiccant Dryer	2.0 - 3.0	hr	
Rear Temperature	160 - 200	°C	
Middle Temperature	170 - 220	°C	
Front Temperature	180 - 240	°C	
Nozzle Temperature	190 - 250	°C	
Processing (Melt) Temp	230	°C	
Mold Temperature	30 - 80	°C	
Injection instructions			

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

If originally sealed containers are used, it is normally possible to omit the predrying stage. If PTFE materials are not predried, an increase in deposits inside the mould may occur.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

Please contact us for further information.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT