

PEXTIN™ RCPETMIG40-BK09

Polyethylene Terephthalate

Pier One Polymers, Inc.

Message:

Pextin™ RCPETMIG40 is available in black only, internal and external lubricants, UV stabilized and other modifications. Manufactured with recycled content. Further information and details are available upon request.

General Information			
Filler / Reinforcement	Glass\Mica,40% Filler by Weight		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.64	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	100	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	2.0	%	ASTM D638
Flexural Modulus (23°C)	9660	MPa	ASTM D790
Flexural Strength (23°C)	166	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	70	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	205	°C	ASTM D648
Peak Melting Temperature	247	°C	ASTM D3418
Injection	Nominal Value	Unit	
Suggested Max Moisture	< 0.020	%	
Processing (Melt) Temp	271 to 299	°C	
Mold Temperature	110 to 121	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT