

Fiberfil® PP-60/CC/30

Polypropylene Homopolymer

Fiberfil® Engineered Plastics Inc.

Message:

Fiberfil® PP-60/CC/30 is a Polypropylene Homopolymer (PP Homopolymer) material filled with 30% calcium carbonate. It is available in North America. Primary attribute of Fiberfil® PP-60/CC/30: Homopolymer.

General Information			
Filler / Reinforcement	Calcium Carbonate,30% Filler by Weight		
Features	Homopolymer		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow			ASTM D955
3.18 mm	1.1	%	
6.35 mm	1.1	%	
Water Absorption (24 hr)	0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	95		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2620	MPa	ASTM D638
Tensile Strength (23°C)	27.6	MPa	ASTM D638
Tensile Elongation (Yield, 23°C)	40	%	ASTM D638
Flexural Modulus - Tangent (23°C)	2450	MPa	ASTM D790
Flexural Strength (23°C)	41.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	27	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	121	°C	
1.8 MPa, Unannealed	73.9	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

