

Laprene® 8K1000A55

Styrene Ethylene Butylene Styrene Block Copolymer

SO.F.TER. SPA

Message:

Laprene® 8K1000A55 is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) material. It is available in Europe, Latin America, or North America.

Primary attribute of Laprene® 8K1000A55: REACH Compliant.

Typical application of Laprene® 8K1000A55: Engineering/Industrial Parts

General Information			
Uses	Overmolding		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 3 sec)	55		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain)	1.80	MPa	ASTM D412
Tensile Strength ²	10.8	MPa	ASTM D412
Tensile Elongation ³ (Break)	580	%	ASTM D412
Tear Strength ⁴	37.0	kN/m	ASTM D624
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Rear Temperature	210	°C	
Middle Temperature	220	°C	
Front Temperature	230	°C	
Nozzle Temperature	230	°C	
Mold Temperature	30.0 to 50.0	°C	
NOTE			
1.	Die C		
2.	Die C		
3.	Die C		
4.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

