

TES J-80/20

Acetal (POM) Copolymer
Techmer Engineered Solutions

Message:

Molding Parameters:
For 2-zone machines, the rear temperature is 360-410°F, and the front temperature is 350-380°F.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Copolymer		
	Good Chemical Resistance		
	Good Dimensional Stability		
	Good Stiffness		
	Good Toughness		
	High Strength		
	Self Lubricating		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.55	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.60	%	ASTM D955
Water Absorption (24 hr)	0.27	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6890	MPa	ASTM D638
Tensile Strength (Yield)	82.7	MPa	ASTM D638
Tensile Elongation (Yield)	2.2	%	ASTM D638
Flexural Modulus	5520	MPa	ASTM D790
Flexural Strength (Yield)	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	163	°C	
1.8 MPa, Unannealed	160	°C	
Injection	Nominal Value	Unit	
Drying Temperature	71.1	°C	

Drying Time	1.0	hr
Rear Temperature	177 to 193	°C
Middle Temperature	188 to 210	°C
Front Temperature	182 to 199	°C
Nozzle Temperature	177 to 204	°C
Processing (Melt) Temp	193 to 216	°C
Mold Temperature	82.2 to 121	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

