

Nycal™ 1850L3H Bk-2

Polyamide 6
Technical Polymers, LLC

Message:

Nycal™1850L3H Bk-2 is a polyamide 6 (nylon 6) material. This product is available in North America and is processed by rotational molding. Nycal™The main characteristics of 1850L3H Bk-2 are: heat stabilizer.

General Information			
Additive	heat stabilizer		
Features	Thermal Stability		
Appearance	Black		
Forms	Particle		
Processing Method	rotomolding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	72.4	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	50	%	ASTM D638
Flexural Modulus (23°C)	2690	MPa	ASTM D790
Flexural Strength (23°C)	96.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	60.0	°C	ASTM D648
Peak Melting Temperature	220	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+14	ohms · cm	ASTM D257
Additional Information	Nominal Value	Unit	
Oven Temperature	299 - 354	°C	
Rotational molding: Nitrogen or Carbon Dioxide purge required during heating cycle to prevent oxidation during processing			
Injection	Nominal Value	Unit	
Drying Temperature	73.9 - 79.4	°C	
Drying Time	3.0 - 4.0	hr	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

