

Tecnoflon® PFR 95HT

Perfluoroelastomer

Solvay Specialty Polymers

Message:

Tecnoflon® PFR 95HT is a perfluoroelastomer (FFKM) offering a significantly wider operational range and superior compression set resistance than any other perfluoroelastomer, thanks to its unique peroxide curing system that does not need any coagent (TAIC or equivalent) for curing to be carried out. It can offer a very broad chemical resistance in a wide variety of media including acids, caustics, ketones, aldehydes, esters, ethers, methanol, solvents, sour gases, hydrocarbons, steam, hot water and mixed process streams along with excellent thermal resistance.

Tecnoflon® PFR 95HT is suitable for most applications in temperature ranging from -10°C to 300°C.

Tecnoflon® PFR 95HT can be combined with other typical fluoroelastomer compounding ingredients; its mixing can be accomplished with two-roll mills or internal mixers. Finished goods may be produced by a variety of rubber processing methods.

The primary use for Tecnoflon® PFR 95HT is the manufacturing of any kind of elastomeric sealing element such as O-rings, gaskets, valve bodies, butterfly valves, pump housings and stators, metal bonded parts, diaphragms, profiles, etc. These sealing elements can be used in mechanical seals, pumps, compressors, valves, reactors, mixers, sprayers, dispensers, quick connect couplings, controls, instrumentation, etc. in chemical and petrochemical industry, hydrocarbon processing, petroleum exploration and extraction, food processing, pharmaceutical and bio-analytical industry, aerospace and semiconductor manufacturing industries.

Tecnoflon® PFR 95HT is registered in the FDA Inventory of Effective Premarket Notifications for Food Contact Substances. It can be compounded so that the finished gaskets or seals can be used in food processing equipments (see "food processing compounds" section below).

Tecnoflon® PFR 95HT is marketed in the form of raw polymer (1 kg box) in order to give the transformer the freedom and the opportunity to develop and fine-tune compounds and items best suited to produce high performance rubber articles such as O-rings, seals, diaphragms and other parts used in process industries.

General Information	
Features	Acid Resistant
	Alcohol Resistant
	Food Contact Acceptable
	Fuel Resistant
	Good Chemical Resistance
	High Heat Resistance
	Low Compression Set
	Moisture Resistant
	Solvent Resistant
	Steam Resistant
Uses	Blending
	Compounding
	Diaphragms
	Gaskets
	Profiles
	Pump Parts
	Seals
Agency Ratings	FDA Food Contact, Unspecified Rating
Appearance	Translucent

Forms	Slab	
Processing Method	Compounding	
Physical	Nominal Value	Unit
Mooney Viscosity ¹ (ML 1+10, 121°C)	75	MU
NOTE		
1.	Raw polymer	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

