

XYLEX™ X7200MR resin

Polycarbonate + Polyester
SABIC Innovative Plastics Europe

Message:
Mold Release version of X7200

General Information			
Additive	Mold Release		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.20	g/cm ³	ASTM D792
--	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (265°C/2.16 kg)	12	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (265°C/2.16 kg)	12.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Flow : 3.20 mm	0.50 to 0.70	%	
Across Flow : 3.20 mm	0.50 to 0.70	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	76		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1880	MPa	ASTM D638
--	2000	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	55.0	MPa	ASTM D638
Yield	55.0	MPa	ISO 527-2/50
Break ³	56.0	MPa	ASTM D638
Break	56.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	5.0	%	ASTM D638
Yield	5.0	%	ISO 527-2/5
Break ⁵	140	%	ASTM D638
Break	> 150	%	ISO 527-2/50
Flexural Modulus			
50.0 mm Span ⁶	1960	MPa	ASTM D790
-- ⁷	2000	MPa	ISO 178
Flexural Stress			

--	75.0	MPa	ISO 178
Yield, 50.0 mm Span ⁸	84.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	900	J/m	ASTM D256
-10°C ⁹	5.0	kJ/m ²	ISO 180/1A
23°C ¹⁰	8.0	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	95.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	96.0	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	90.0	°C	ASTM D648
1.8 MPa, Unannealed, 100 mm Span ¹¹	99.0	°C	ISO 75-2/Ae
Vicat Softening Temperature	115	°C	ISO 306/B120, ASTM D1525 ¹²
Ball Pressure Test ¹³ (105°C)	Pass		IEC 60695-10-2
CLTE			
Flow : -40 to 40°C	1.1E-4	cm/cm/°C	ASTM E831
Flow : 23 to 60°C	8.0E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	1.1E-4	cm/cm/°C	ASTM E831
Transverse : 23 to 60°C	8.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.23	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	ASTM D257
Volume Resistivity	> 1.0E+15	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	V-2		UL 94
Glow Wire Flammability Index (1.00 mm)	750	°C	IEC 60695-2-12
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.557		ISO 489
Transmittance (2540 µm)	88.0	%	ASTM D1003
Haze (2540 µm)	1.1	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	82.2 to 93.3	°C	
Drying Time	3.0 to 5.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 80	%	
Rear Temperature	238 to 249	°C	
Middle Temperature	243 to 266	°C	
Front Temperature	249 to 271	°C	
Nozzle Temperature	249 to 271	°C	

Processing (Melt) Temp	249 to 271	°C
Mold Temperature	43.3 to 60.0	°C
Back Pressure	0.172 to 0.517	MPa
Screw Speed	20 to 100	rpm
Vent Depth	0.013 to 0.020	mm

NOTE

1.	50 mm/min
2.	Type I, 50 mm/min
3.	Type I, 50 mm/min
4.	Type I, 50 mm/min
5.	Type I, 50 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4
10.	80*10*4
11.	120*10*4 mm
12.	Rate B (120°C/h), Loading 2 (50 N)
13.	Approximate maximum

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT