

New-prene™ 9265N

Polypropylene + EPDM Rubber

Total Polymer Vision (Suzhou) Co., LTD

Message:

A soft, natural color EPDM/PP thermoplastic vulcanizate. This material has good adhesive to PA. It can be overmolded to PA or PA/30%glass fiber. It is EU directive 2002/95/EC (RoHS) compliant. It is polyolefin based and completely recyclable.

General Information			
Features	Good Adhesion		
	Recyclable Material		
	Soft		
Uses	Overmolding		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	65		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	4.50	MPa	ASTM D412
Tensile Elongation (Break)	480	%	ASTM D412
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-55.0	°C	ASTM D746
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Rear Temperature	165	°C	
Middle Temperature	165 to 190	°C	
Front Temperature	170 to 220	°C	
Nozzle Temperature	180 to 230	°C	
Processing (Melt) Temp	170 to 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

