

Surlyn® 1825

Ionomer

DuPont Packaging & Industrial Polymers

Message:

Surlyn® 1825 is available for use in conventional blown, cast film, sheet extrusion and coextrusion equipment designed to process polyethylene and ethylene copolymer type resins.

General Information			
Features	Compliance of Food Exposure		
Uses	Films cast film Sheet		
Agency Ratings	FDA 21 CFR 177.1330(a)		
Processing Method	Blow film Co-extrusion molding cast film Sheet extrusion molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.940	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.4	g/10 min	ASTM D1238, ISO 1133
Ion Type	Zinc		
Freezing Point			
--	76	°C	ISO 3146
--	76	°C	ASTM D3417

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	73.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	97.0	°C	ASTM D3417, ISO 3146

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	135	°C
Cylinder Zone 2 Temp.	160	°C
Cylinder Zone 3 Temp.	185	°C
Cylinder Zone 4 Temp.	185	°C
Cylinder Zone 5 Temp.	185	°C
Adapter Temperature	185	°C
Melt Temperature	160 - 285	°C
Die Temperature	185	°C

Extrusion instructions

The above processing values are for blown film.Cast film/sheet parameters:

Feed Zone: 160°C

Second Zone: 185°C

Third Zone: 210°C

Fourth Zone: 210°C

Fifth Zone: 210°C

Adapter Zone: 210°C

Die Zone: 210°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

