# SUNIGUM® P95

### Acrylic

**Omnova Solutions Inc.** 

#### Message:

Acrylate Terpolymer KEY ADVANTAGES Resistant to heat & UV radiation Chemical, oil & fuel resistance Tailor made TPE's that offer softness, matte surface finish, leather-like appearance, color retention and weatherability APPLICATIONS Plastic modification in thermoplastic melt blends: PVC, CPE, COPE, TPU, ASA/ABS/SAN and other polymers with some polarity such as olefin copolymers like EVA and EMA Overmolded & co-extruded TPE's: auto interior skins, auto profiles & moldings, building gaskets, coated fabrics & roofing, hoses & tubing, skins & leather, wires & cable Additional Feature: Good compatibility with TPU, PVC, COPE, ABS and SAN

General Information				
Additive	Processing Aid			
Features	Fuel Resistant			
	Good Chemical Resistance			
	Good Surface Finish			
	Good UV Resistance			
	High Heat Resistance			
	Oil Resistant			
Uses	Appliance Components			
	Automotive Applications			
	Automotive Exterior Parts			
	Automotive Exterior Trim			
	Automotive Interior Parts			
	Automotive Interior Trim			
	Cable Jacketing			
	Consumer Applications			
	Footwear			
	Gaskets			
	Glazing			
	Hose			
	Membranes			
	Overmolding			
	Profiles			
	Seals			
	Tubing			

RoHS Compliance	RoHS Compliant
Appearance	Off-White
Forms	Powder
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm³	
Mooney Viscosity (ML 1+4, 150°C)	25	MU	
Particle Size	800	μm	
Partitioned With	Calcium Carbonate		
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	53		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-25.0 to -18.0	°C	ASTM E1356

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

