

# NYCOA Polyamide 2061

Polyamide 66/6 Copolymer  
Nycoa (Nylon Corporation of America)

Message:

NYCOA 2061 is a Nylon copolymer developed specially for applications that demand easy flow, toughness, and flexibility. Its moderately high melt viscosity processes easily on conventional extrusion equipment and yields products with extremely high tenacity. NYCOA 2061 is available with custom additive packages: heat stabilizer, UV stabilizer, flame retardant and/or customer colors. Typical applications include premium weed-eater monofilament and fishing line.

General Information			
Features	High tensile strength		
	High strength		
	Copolymer		
	Workability, good		
	Good liquidity		
	Good flexibility		
	Good toughness		
	Medium and high viscosity		
Uses	monofilament		
	Fishery application		
Appearance	Available colors		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm <sup>3</sup>	ASTM D792
Water Absorption (24 hr)	2.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup>	60.0	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	300	%	ASTM D638
Flexural Modulus <sup>3</sup>	1030	MPa	ASTM D790
Flexural Strength <sup>4</sup>	44.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (6.35 mm)	43	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	199	°C	DSC
Additional Information			
Relative Viscosity, NYCOA Method: 4 SAVWater Extractable, NYCOA Method: 8 to 10 %Tensile Elongation at Break, ASTM D638, 2 in/min: 300+%The value listed as Melting Point DSC, was tested in accordance with ASTM D789.			
NOTE			

1.	51 mm/min
2.	51 mm/min
3.	51 mm/min
4.	51 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

