

# MAJORIS DG308X - 8229

Polypropylene

AD majoris

## Message:

MAJORIS DG308X - 8229 is a high performance reinforced polypropylene compound intended for injection moulding.

The product is available in natural, but other colours can be provided on request.

MAJORIS DG308X - 8229 has been developed especially for demanding applications in various engineering sectors.

MAJORIS DG308X - 8229 has high rigidity and impact strength, good dimensional stability, very good stiffness and good creep resistancy also at high temperatures.

## APPLICATIONS

Product requiring very high overall mechanical performance such as:

Electrical tool and appliance components

Under the bonnet parts

Miscellaneous technical items

General Information			
Features	Good dimensional stability		
	Rigidity, high		
	Rigidity, high		
	Impact resistance, high		
	Recyclable materials		
	Good creep resistance		
Uses	Electrical/Electronic Applications		
	Power/other tools		
	Home appliance components		
	Parts under the hood of a car		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.5	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction: 2.00mm	1.0	%	Internal method
Flow direction: 2.00mm	0.20	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9600	MPa	ISO 527-2/1
Tensile Stress (Yield)	122	MPa	ISO 527-2/50

Tensile Strain (Break)	2.7	%	ISO 527-2/50
Flexural Modulus <sup>1</sup>	8000	MPa	ISO 178
Flexural Stress	190	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	62	kJ/m <sup>2</sup>	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	169	°C	ISO 75-2/B
1.8 MPa, not annealed	162	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	230 - 270	°C	
Mold Temperature	30.0 - 60.0	°C	
Injection Rate	Moderate		
Holding Pressure	30.0 - 60.0	MPa	
Injection instructions			
Screw speed: Low to mediumBack pressure: Low to medium			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT