

Nypol® PA A3 T40 HL CNZA0040 NR359

Polyamide 66

Petropol Industry and Trade of Polymers LTDA

Message:

Nypol® PA A3 T40 HL CNZA0040 NR359 is a Polyamide 66 (Nylon 66) material filled with 40% talc. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Nypol® PA A3 T40 HL CNZA0040 NR359 are:

Flame Rated

Lubricated

General Information			
Filler / Reinforcement	Talc,40% Filler by Weight		
Additive	Lubricant		
Features	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.90 to 1.0	%	ASTM D955
Water Absorption (24 hr)	1.3	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	85.0	MPa	ASTM D638
Tensile Elongation (Break)	15	%	ASTM D638
Flexural Modulus	5100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	90.0	°C	ASTM D648
Melting Temperature	260	°C	ASTM D2117
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	70.0 to 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

