Kepex® 3300SC

Polybutylene Terephthalate

Korea Engineering Plastics Co., Ltd

Message:

KEPEX 3300SC is an unfilled, impact modified, and high melt flow PBT. It exhibits good toughness and impact strength. It is applicable to automotive, electrical, electronic, and industrial parts.

General Information					
Additive	Impact Modifier				
Features	Good Impact Resistance				
	Good Toughness				
	Impact Modified				
Uses	Automotive Applications				
	Electrical Parts				
	Electrical/Electronic Applications				
	Industrial Applications				
Forms	Pellets				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.30	g/cm³	ASTM D792		
Melt Mass-Flow Rate (MFR) (250°C/2.16					
kg)	50	g/10 min	ASTM D1238		
Molding Shrinkage - Flow (3.00 mm)	1.8 to 2.2	%	ASTM D955		
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale)	117		ASTM D785		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield, 23°C)	51.0	MPa	ASTM D638		
Tensile Elongation (Break, 23°C)	150	%	ASTM D638		
Flexural Modulus (23°C)	2210	MPa	ASTM D790		
Flexural Strength (23°C)	75.5	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (23°C)	43	J/m	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		
Deflection Temperature Under Load			ASTM D648		
0.45 MPa, Unannealed	150	°C			
1.8 MPa, Unannealed	50.0	°C			
Melting Temperature	220	°C	DSC		
Flammability	Nominal Value		Test Method		

Flame Rating (0.800 mm)	НВ	НВ	
Injection	Nominal Value	Unit	
Hopper Temperature	230 to 250	°C	
Rear Temperature	230 to 250	°C	
Middle Temperature	230 to 250	°C	
Front Temperature	230 to 250	°C	
Nozzle Temperature	230 to 250	°C	
Mold Temperature	40.0 to 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

