

Geon™ Vinyl Fittings M1000

Rigid Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™ Vinyl Fittings M1000 is a Rigid Polyvinyl Chloride product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon™ Vinyl Fittings M1000 include plumbing/piping/potable water and engineering/industrial parts. Primary characteristic: flame rated.

General Information			
UL YellowCard	E41877-234272		
Features	Medium Flow		
Uses	Fittings		
Agency Ratings	NSF 14		
	NSF 61		
	NSF Type I 4		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Spiral Flow	63.5	cm	
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
PVC Cell Classification	12454		ASTM D1784
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	81		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	3030	MPa	ASTM D638
Tensile Strength ² (Yield)	49.6	MPa	ASTM D638
Flexural Modulus	3100	MPa	ASTM D790
Flexural Strength	91.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256A
23°C, 3.18 mm, Injection Molded	53	J/m	
23°C, 6.35 mm, Injection Molded	37	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.35 mm	72.8	°C	
1.8 MPa, Unannealed, 6.35 mm	72.2	°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm, ALL)	V-0		UL 94
Injection	Nominal Value	Unit	

Processing (Melt) Temp	199 to 210	°C
NOTE		
1.	Type I, 51 mm/min	
2.	Type I, 51 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

