

Elvaloy® AC 15024S

Ethylene Methyl Acrylate Copolymer

DuPont Packaging & Industrial Polymers

Message:

Elvaloy® AC 15024S is a copolymer of ethylene and methyl acrylate. It is available in pellet form for use in conventional extrusion equipment designed to process polyethylene type resins.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
Agency Ratings	FDA 21 CFR 177.1340(a)		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.944	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	50	g/10 min	ASTM D1238, ISO 1133
Methyl Acrylate Content	24.0	wt%	
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	88.0	°C	ASTM D3418, ISO 3146
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	135	°C	
Cylinder Zone 2 Temp.	185	°C	
Cylinder Zone 3 Temp.	210	°C	
Cylinder Zone 4 Temp.	210	°C	
Cylinder Zone 5 Temp.	210	°C	
Adapter Temperature	210	°C	
Melt Temperature	185 to 235	°C	
Die Temperature	210	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT