

HiFill® HDPE GF15 50100

High Density Polyethylene

Techmer Engineered Solutions

Message:

HiFill® HDPE GF15 50100 is a High Density Polyethylene product filled with 15% glass fiber. It can be processed by extrusion and is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.70	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	55.2	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	4070	MPa	ASTM D790
Flexural Strength	68.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	190	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	129	°C	
1.8 MPa, Unannealed	121	°C	
CLTE - Flow	5.4E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength ¹	12	kV/mm	ASTM D149
Injection	Nominal Value	Unit	
Drying Temperature	76.7	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	232 to 260	°C	
Middle Temperature	232 to 260	°C	
Front Temperature	232 to 260	°C	

Processing (Melt) Temp	218 to 246	°C
Mold Temperature	26.7 to 48.9	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	30 to 60	rpm

NOTE

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

