

# Globalene® 8888

Polypropylene Random Copolymer  
Lee Chang Yung Chemical Industry Corp.

Message:

Globalene® 8888 is a Polypropylene Random Copolymer (PP Random Copolymer) material. It is available in Asia Pacific or North America for injection molding.

Important attributes of Globalene® 8888 are:

Clarity  
Copolymer  
High Flow  
Impact Resistant

Typical applications include:

Appliances  
Household Applications

General Information			
Features	High Clarity		
	High Flow		
	Low Temperature Impact Resistance		
	Random Copolymer		
Uses	Appliances		
	Household Goods		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.896	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	46	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.2	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	86		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	29.4	MPa	ASTM D638
Tensile Elongation (Yield)	12	%	ASTM D638
Flexural Modulus	1060	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	41	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	88	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT