

Elvaloy® AC 1913

Ethylene Methyl Acrylate Copolymer

DuPont Packaging & Industrial Polymers

Message:

Elvaloy® AC 1913 is a copolymer of ethylene and methyl acrylate. It is available in pellet form for use in conventional extrusion equipment designed to process polyethylene type resins.

13% Methyl Acrylate

General Information	
Features	Copolymer
Agency Ratings	FDA 21 CFR 177.1340(a)
Forms	Pellets
Processing Method	Coextrusion Extrusion Coating

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ASTM D1238, ISO 1133
Methyl Acrylate Content	13.0	wt%	

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	60.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	98.0	°C	ASTM D3418, ISO 3146

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	185	°C
Cylinder Zone 2 Temp.	235	°C
Cylinder Zone 3 Temp.	260	°C
Cylinder Zone 4 Temp.	285	°C
Cylinder Zone 5 Temp.	285	°C
Adapter Temperature	285	°C
Melt Temperature	235 to 310	°C
Die Temperature	285	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

