

Edgetek™ ET3500-5002 BK

Acrylonitrile Styrene Acrylate + PC

PolyOne Corporation

Message:

The Edgetek™ Engineering Thermoplastic Compounds portfolio covers a broad range of standard and custom-formulated high performance materials. This portfolio includes high-temperature materials for elevated service temperature environments, high-modulus / structural materials for load-bearing and high-strength applications and flame-retardant products. These compounds are based on select engineering thermoplastic resins that are compounded with reinforcing additives such as carbon fiber, glass fiber and glass beads.

General Information			
Filler / Reinforcement	Glass Fiber, 12% Filler by Weight		
Features	Low Warpage		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density ¹ (23°C)	1.23	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/2.16 kg)	17 to 22	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/21.6 kg)	13.0 to 16.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow	0.10 to 0.20	%	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C, 4.00 mm, Injection Molded)	5900	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C, 4.00 mm, Injection Molded)	100	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C, 4.00 mm, Injection Molded)	2.2	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C, Injection Molded)	8.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C, Injection Molded)	37	kJ/m ²	ISO 179
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257
Volume Resistivity	> 1.0E+15	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	280 to 320	°C	

Mold Temperature	82.0 to 110	°C
NOTE		
1.	±0.02	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

