

GERMAFORM 9 GF 10

Acetal (POM) Copolymer

Kunststoff-Kontor-Hamburg GmbH

Message:

GERMAFORM 9 GF 10 is an Acetal (POM) Copolymer material filled with 10% glass fiber. It is available in Europe.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.48	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)	6.00	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4400	MPa	ISO 527-2
Tensile Stress (Break)	90.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	35	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	
Melting Temperature	166	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT