

OnFlex™ S HF 90A-3S1988

Thermoplastic Elastomer

PolyOne Corporation

Message:

OnFlex™-S HF thermoplastic elastomer polymer is mixed with hydrogenated styrene block copolymer. This series of polymers uses a unique, patent-pending halogen-free flame retardant system. And, OnFlex™-S HF polymer has good mechanical properties, meets the requirements of UL94 V-0, has good oxygen limit index (LOI) value, large hardness range, good processability, and excellent stability to ultraviolet rays.

General Information			
Features	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Industrial application		
	Application in Automobile Field		
	Business equipment		
	General		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	90		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% strain	3.60	MPa	ISO 37
300% strain	5.10	MPa	ISO 37
Tensile Stress (Break)	7.00	MPa	ISO 37
Tensile Elongation (Break)	450	%	ISO 37
Tear Strength	40	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	33	%	ISO 815
70°C, 22 hr	60	%	ISO 815
100°C, 22 hr	81	%	ISO 815
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (2.00 mm)	725	°C	IEC 60695-2-13
Oxygen Index	40	%	ISO 4589-2

Additional Information	Nominal Value	
General Material Type	Styrene thermoplastic elastomers (TES)	
各项属性值是采用注射模制基板测量得出.		
Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	2.0	hr
Processing (Melt) Temp	160 - 180	°C
Mold Temperature	30.0 - 50.0	°C
Injection Rate	Moderate-Fast	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

