

Resinoid 2002-2

Phenolic

Resinoid Engineering Corporation

Message:

Resinoid 2002-2 is a Phenolic product filled with filler. It can be processed by compression molding, injection molding, or resin transfer molding and is available in North America. Applications of Resinoid 2002-2 include automotive and electrical/electronic applications.

Characteristics include:

Good Dimensional Stability

Impact Resistant

General Information	
Filler / Reinforcement	Filler
Features	Good Dimensional Stability
	Good Impact Resistance
Uses	Automotive Applications
	Electrical Parts
Appearance	Black
Forms	Pellets
Processing Method	Compression Molding
	Injection Molding
	Resin Transfer Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Bulk Factor	10		ASTM D1895
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	55.2	MPa	ASTM D638
Flexural Modulus	11000	MPa	ASTM D790
Flexural Strength (Yield)	102	MPa	ASTM D790
Compressive Strength	138	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	72	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	260	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Arc Resistance	180	sec	ASTM D495

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

