

Sumiflex® K K768DB6

Polyvinyl Chloride Elastomer
Mitsubishi Chemical Corporation

Message:

Sumiflex® K K768DB6 is a Polyvinyl Chloride Elastomer (PVC Elastomer) material. It is available in Asia Pacific for injection molding.
Important attributes of Sumiflex® K K768DB6 are:
Chemical Resistant
Flame Retardant
Typical application of Sumiflex® K K768DB6: Automotive

General Information			
Features	Flame Retardant		
	Oil Resistant		
Uses	Automotive Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm³	JIS K7112
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (10 sec)	48		JIS K6253
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	3.00	MPa	JIS K6723
Tensile Stress (Break)	13.0	MPa	JIS K6723
Tensile Elongation (Break)	460	%	JIS K6723

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

