

# Eleme NGL020FG

Linear Low Density Polyethylene  
Eleme Petrochemical Company Ltd

Message:

NGL020FG is a Butene Co-monomer based Liner Low Density Polyethylene Resin manufactured by IEPL using "SCLAIRTECH" solution polymerisation process of DU Pont, Canada (Now Nova Chemicals) offers narrow molecular weight distribution copolymer without slip & antiblock additive which has been specifically designed for the production of Blown film as well as high strength cast film, air bubble film and film for lamination application.

General Information			
Features	Low speed solidification crystal point		
	High strength		
	Optical		
	Narrow molecular weight distribution		
Uses	Blown Film		
	Films		
	Laminate		
	Lining		
	Stretch winding		
	cast film		
Appearance	Natural color		
Processing Method	Film extrusion		
	Blow film		
	Co-extruded film		
	cast film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.919	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882
MD: Yield	12.5	MPa	ASTM D882
TD: Yield	12.0	MPa	ASTM D882
MD: Fracture	30.0	MPa	ASTM D882
TD: Fracture	25.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	700	%	ASTM D882
TD: Fracture	800	%	ASTM D882
Additional Information	Nominal Value	Unit	Test Method

Dart Impact	29.4	kN/m	ASTM D1709
Tear Strength			ASTM D1922
MD	19.6	kN/m	ASTM D1922
TD	71.6	kN/m	ASTM D1922

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

