

VAMPLUB C 00U 10TFSi

Polycarbonate

Vamp Tech

Message:

PC unfilled with PTFE and silicon.

General Information			
Additive	PTFE + Silicone Lubricant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.80	%	
Across Flow	0.80	%	
Water Absorption (Saturation)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ASTM D638
Tensile Strength (Yield)	50.0	MPa	ASTM D638
Tensile Elongation (Break)	> 10	%	ASTM D638
Coefficient of Friction			ASTM D1894
Dynamic	0.11		
Static	0.16		
Wear Factor ¹	34.0	10 ⁻¹⁰ m ³ h/N·m·h	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	20	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	65	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	125	°C	ASTM D648A
Vicat Softening Temperature	145	°C	ASTM D1525 ²
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	V-2		
3.20 mm	V-2		
NOTE			
1.	Thrust Washer		
2.	Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

